# **Evaporation Materials**

# **LUMILEAD TNO**

### **Characteristic**

- ◆Antistatic properties are imparted, preventing the adhesion of dust and dirt.
- ◆Continuous evaporation can be performed by replenishing the material.
- ◆ The material has a granular shape and therefore is easily melted.
- ◆ The deposited film has a greater refractive index than that of ITO.





non coat

coated

## **Application**















Glasses

Auto motive

Camera

display

LCD projector

Microscope

Cosmetics

### **Performance**

#### **Electrostatic Potential Measurement**

Conditions	Substrate with AR Coating I (Titanium Oxide Materials) [kV]	Substrate with AR Coating II (LUMILEAD TNO) [kV]
Before rubbing	0.00	0.00
Immediately after rubbing with cotton for 10 seconds	-0.39	-0.08
1 min. after rubbing	-0.27	-0.03
2 min. after rubbing	-0.18	-0.02

#### **Sheet Resistance, Absorption**

Evaporation Material	Sheet Resistance [Ω/□]	Absorption (@500nm)[%]
LUMILEAD TNO	1.7×10 <sup>9</sup>	1.75
Titanium Oxide Materials	5.5×10 <sup>11</sup>	0.32

Values described in this document are actual measurements, not product specification values.

Please note that we are not liable for any loss or damage arising from the use of the information in this document. Please make sure that this product is fit for purpose, including performing preliminary tests, before starting to use it.

## **Product Lineup**

Product Name	Form	Size
LUMILEAD TNO	Amorphous granular	0.1-1.7 [mm]



Appearance

# **Deposition Condition Examples**

<b>Deposition Conditions</b>	
Chamber diameter	Ф1,300 [mm]
Evaporation source	Electron beam
Oxygen introduction	None
lon assist (IAD)	Voltage: 550 [V] Current: 550 [mA] $O_2$ Flow rate: 40 [sccm]
Evaporating distance	1100 [mm]
Substrate heating	No heating
Evaporation rate	4 [Å/s]
Film thickness	100[nm]
Degree of vacuum at start of evaporation	9.0×10 <sup>-4</sup> [Pa] or lower
Substrate to be vapor-deposited, size	Optical glass BK7 Φ74.5 × t 1.1 [mm]

Electron beam Conditions				
	AMP. [ - ]	Emission current [mA]	Time [min'sec]	
Pre-melting	5.0	400→580→410	1′05"	
Evaporation	0.0	Rate control	_	

- All the data listed in this Pamphlet Data are either values measured by our company or quoted from the literature. However, we cannot accept any liability for any troubles or damage caused by using any of these data.
- In order to use the product safely and correctly, please first read the Product Safety Data Sheet.
- Pamphlet Data contained herein is the data as of December 2022.
- Note that the specifications of this Pamphlet Data and/or product appearance are subject to change for improvement, etc. without prior notice.
- We reserve all rights to this Pamphlet Data.
- Please contact us for any inquiries/requests about the product, for more details, or for product catalogs, etc.



1744-1, Kanakubo, Yuki, Ibaraki 307-0015 Japan

TEL: +81-296-21-3700 FAX: +81-296-21-3770

E-mail: optsales@mail.canon URL: https://optron.canon/en/

